# nstrnm 9



Made with 95% post-consumer recycled material

### PROCESSING OF OSTROM 95

Suitable for Extrusion, Injection Molding, Compression Molding & Thermoforming Processing temperature range 460°F to 550°F (235°C to 285°C)

#### PROPERTIES OF OSTROM 95

ASTM	OSTROM 95
Melt Index	16 (g/10 min@285°C/2.16 Kg)
Density	1.31 g/cm
Tensile Strength @ yield	3,249 psi
Tensile Modulus	151,564 psi
Flexural Strength	4,699 psi
Flexural Modulus	147,068 psi
Heat Deflection Temperature	147°F
Vicat softening temperature	356℉
Shore D	67
Dielectric Strength	678 V/Mil

(In accordance with ASTM: D792, D638, D790, D648, D2240, D1525, D3418, D2863, D149, F1249)

#### **PACKAGING AVAILABLE**

- 55lb bag
- 1500lb gaylord

## BENEFITS OF OSTROM



- All our raw materials are locally and reliably sourced, and available in FDA compliant grades. We are focused on reducing our carbon footprint through local manufacturing of the product and product delivery from our centrally located warehouse
- Our resin blends undergo a reactive extrusion process, allowing us to break barriers when it comes to utilization of recycled content. Our high-quality recycled resin blend offers no contamination and a high degree of batch-to-batch consistency - unlike regrind
- Ostrom offers a unique chemistry allowing our materials to display superior mechanical properties, including excellent barrier properties, offering sustainable benefits in packaging applications, and excellent tensile and impact strength allowing us to replace engineering resins at a competitive price with sustainable advantages.
- With four available grades of Ostrom we offer a versatility of products across several industries. Products are also available with additives and fillers upon request (UV stabilizer, antioxidant, carbon black, talc, glass) - please ask for details.



#### POTENTIAL APPLICATIONS FOR OSTROM 95

- Automotive Components under-the-hood parts, interior panels, or structural components that require durability and heat resistance.
- 🕅 High-Performance Packaging electronics, and applications where thermal stability is important.
- (Y) Electrical and Electronic Components electronic housings, connectors, and components that need to withstand heat and mechanical stress.
- Furniture and Consumer Goods furniture components, durable consumer goods, or other products where longevity and material strength are important.
- 🔇 Industrial Applications gears, bearings, or high-strength parts that require rigidity, wear resistance, and thermal stability.
- ♥ Construction Materials panels, fittings, or profiles that require strength and environmental responsibility.

PH: 281-492-8418 SALES: 832-740-3117